

Effect of Magnetic Impurities in Crystalline and Amorphous States of Superconductors

Mi-Ae Park

*Department of Physics, University of Puerto Rico at Humacao,
Humacao, PR 00791*

Kerim Savran and Yong-Jihn Kim

*Department of Physics, Bilkent University,
06533 Bilkent, Ankara, Turkey*

Abstract

It has been observed that the effect of magnetic impurities in a superconductor is drastically different depending on whether the host superconductor is in a crystalline or an amorphous state. Based on the recent theory of Kim and Overhauser, it is shown that as the system is getting disordered, the initial slope of the T_c depression is decreasing by a factor $\sqrt{\ell/\xi_0}$, when the mean free path ℓ becomes smaller than the BCS coherence length ξ_0 , which is in agreement with experimental findings. In addition, for a superconductor in a pure crystalline state the superconducting transition temperature T_c drops sharply from about 50% of T_{c0} (for a pure system) to zero near the critical impurity concentration. This *pure limit behavior* was indeed found by Roden and Zimmermeyer in crystalline Cd.

PACS numbers: 74.60.Mj, 74.20.-z, 74.90.+n

I. INTRODUCTION

It has been well appreciated among experimentalists that the effect of magnetic impurities in superconductors depends strongly on whether the host superconductor is in the crystalline state or in the amorphous state.¹⁻¹⁰ For instance, the initial slope of the T_c decrease due to magnetic impurities is not universal but dependent on the sample quality and sample preparation methods. This was not well understood. Kim and Overhauser (KO)¹¹ have recently proposed a theory of magnetic impurity effect on superconductors, which anticipates the above experimental observations. To summarize, they obtained the following results:

(1) The initial slope of the T_c decrease due to magnetic impurities depends on the superconductor and therefore is not a universal constant.

(2) The reduction of T_c by magnetic impurities is significantly lessened whenever the mean free path ℓ becomes smaller than the BCS coherence length ξ_0 .

(3) If the host superconductor is pure enough for exchange scattering to dominate, T_c drops suddenly from about 50 % of T_{c0} (for the pure metal) to zero near the critical impurity concentration. This may be called the *pure limit behavior*.⁷

The second result, called compensation phenomenon, has been observed by adding non-magnetic impurities^{1,2} and radiation damage.^{4,5,8} Indeed, Park, Lee, and Kim¹² showed that KO theory leads to a good fitting to the experimental data obtained from radiation damage.⁸ There is also compelling evidence for the first result. For example, the observed initial decrease of T_c for superconductors as a function of the concentration c of the magnetic ions is bigger in the crystalline state than that in the amorphous state of superconductors. This behavior is also related to the second result. In Table I, most of the values from the literature for the initial decrease of T_c for the Zn-Mn system are listed, which shows this behavior spectacularly. Data are from Falke et al.¹³ As can be seen, the initial slope of the T_c decrease by magnetic impurities is not universal but dependent on the sample quality and sample preparation methods. Note that Zn-Mn alloys show all the Kondo anomalies at low temperatures.¹⁹ The *pure limit behavior* is hard to observe experimentally due to the metallurgical problems related to a very small solubility of magnetic impurities in non-transition metals. Also adding many magnetic impurities may make the host superconductors disordered. Therefore, it is really remarkable that Roden and Zimmermeyer⁶ confirmed the third result, the *pure limit behavior*, in crystalline Cadmium doped with dilute Mn atoms by quench condensation. It is well known that sample preparation of thin-film alloys by evaporation on cold substrates (quench condensation) is suitable for producing alloys between otherwise insoluble components. They prepared (micro)crystalline and amorphous cadmium with dilute Mn impurities. Remarkably, they found that a quench-condensed film of cadmium in the microcrystalline state shows an abrupt decrease of the transition temperature near the critical impurity concentration. Similar *pure limit behavior* has been found in superfluid He-3 in aerogel.²⁰⁻²² In this case, aerogel acts like impurities and decreases the transition temperature of the superfluid He-3. It is straightforward to apply KO theory to p-wave pairing states. More details will be published elsewhere.

In this paper we use KO theory to explain the difference of the magnetic impurity effect in crystalline and amorphous states of superconductors. We find a good agreement with the existing experimental data. A brief review of experimental works is given in Sec. II, while KO theory is described in Sec. III. Comparison with various experimental data is given in

Sec. IV. The *pure limit behavior* will be emphasized.

II. MAGNETIC IMPURITY EFFECT IN CRYSTALLINE AND AMORPHOUS STATES OF SUPERCONDUCTORS

In this Section, the experimental data for the effect of magnetic impurities in a crystalline and an amorphous state of superconductors are briefly reviewed. Although there are already a few review articles on magnetic impurity effect in superconductors,^{23,24} this topic was not spotlighted before, simply because the experimental data were not understood. Nevertheless, it was observed by many experimentalists that the magnetic impurity effects are different for crystalline and amorphous states of superconductors. To illustrate, the initial decrease of T_c for some superconductors as a function of the concentration c of the magnetic ions is summarized in Table II. The Table is from Buckel,¹⁰ Wassermann,³ and Schwidtal.²⁵ It is clear that the initial T_c decrease depends on the sample quality and is not the universal constant suggested by Abrikosov and Gor'kov.²⁶ Note that In-Mn,^{4,5,8} Sn-Mn,²⁸ Zn-Mn,¹³ and Cd-Mn³⁵ show the Kondo anomalies at low temperatures.

Merriam, Liu, and Seraphim¹ were the first who found the difference. They investigated the effect of dissolved Mn on superconductivity of pure and impure In. They observed that the addition of a third element, Pb or Sn, progressively decreases the effect of Mn and eliminates the effect completely when the mean free path is decreased sufficiently enough. In other words, the T_c depression arising from a paramagnetic solute turned out to be mean-free-path dependent. Boato, Gallinaro, and Rizzuto² confirmed the result. It was also found that T_c depression by transition metal impurities in bulk metals and thin films leads very often to different results.³ For instance, broad scattering of the experimental $-dT_c/dc$ values was frequently obtained, presumably due to the differences in the degree of disorder. A review was given by Wassermann.³ On the other hand, Falke et al.¹³ investigated transition temperature depression in quench condensed Zn-Mn dilute alloy films and compared it with bulk data. Their work gives good support to the equivalence of thin films and bulk material. To put it another way, even though the initial T_c depression caused by magnetic impurities may be different for thin films and bulk material, a magnetic impurity may possess a stable magnetic moment whether it is in thin films or in bulk material. Bauriedl and Heim⁴ noted that the reason for the different behavior of a magnetic impurity in crystalline and disordered materials is lattice disorder. The authors considered annealed In films implanted with 150 keV-Mn ions at low temperatures and increased the lattice disorder by pre-implantation of In ions, which led to the variation of the initial T_c -depression between 26 K/at % for the crystalline sample and 10 K/at % for the heavily disordered sample. Hitzfeld and Heim⁵ reported that the magnetic state of Mn in ion implanted In-Mn alloys is not so much affected by incorporating oxygen (lattice disorder) but the superconducting properties changes significantly, in agreement with Falke et al.¹³: $-dT_c/dc$ is changed from 24 to 18 K/at% if oxygen is added. Schlabititz and Zaplinski⁷ reported on the influence of lattice defects on the T_c -depression in dilute Zn-Mn single crystals. Their measurements also show a much higher depression of T_c for single crystals than for cold-rolled crystals and quench-condensed films. Hofmann, Bauriedl, and Ziemann⁸ also observed compensation of the paramagnetic impurity effect as a consequence of radiation damage. Well annealed In-films implanted at low temperatures with Mn ions lead to an initial slope of 50 K/at %, whereas

In-films irradiated with high fluences of Ar ions before the Mn-implantation lead to a slope of 39 K/at %. In addition, 90% of the 2.2 K decrease in T_c caused by Mn-implantation was suppressed by an Ar fluence of $2.2 \times 10^{16} \text{ cm}^{-2}$. Habisreuther et al.⁹ reported on an *in situ* low-temperature ion-implantation study of Mn in crystalline β -Ga and amorphous α -Ga films. They found linear T_c decreases in α -Ga films with a slope of 3.4 K/at % and in β -Ga films with a slope of 7.0 K/at %, (i.e., twice as large as in α -Ga).

Furthermore, Roden and Zimmermeyer⁶ considered crystalline and amorphous cadmium with dilute Mn atoms. In the first case the initial depression of T_c is $-dT_c/dc=5.4$ K/at % and in the second case $-dT_c/dc=2.65$ K/at % in accordance with other results. Surprisingly, a sudden drop of T_c in crystalline cadmium near the critical concentration was observed. About 50 % of T_{c0} was decreased to zero by adding additional tiny amounts of Mn atoms in the (micro)crystalline state, which has been predicted by Kim and Overhauser. Since the transition temperature of pure Cd in the crystalline state is 0.9 K (T_{c0}), the critical Mn impurity concentration is so low (~ 0.075 at %) that the crystalline state is not much disturbed by Mn atoms. Consequently, the *pure limit behavior* of magnetic impurity effect was observable. Zimmermeyer and Roden³⁶ also found similar behavior in microcrystalline films of lead doped with Mn, but with a peak just before T_c drops to zero suddenly. The critical concentration is ~ 0.4 at %. In this case, since the initial T_c depression is not linear as a function of Mn concentration, there seems to be some solubility problem.

III. THEORY OF KIM AND OVERHAUSER

A. Ground state wavefunction

For a homogeneous system, the BCS wavefunction is given by^{37,38}

$$\tilde{\phi} = \prod_k (u_k + v_k a_{k\uparrow}^\dagger a_{-k\downarrow}^\dagger) \phi_0 \quad (1)$$

where the operator $a_{k\alpha}^\dagger$ creates an electron in the state $(k\alpha)$ (with the energy ϵ_k) when operating on the vacuum state designated by ϕ_0 . Note that $\tilde{\phi}$ is an approximation of ϕ_N ,

$$\phi_N = A[\phi(r_1 - r_2) \cdots \phi(r_{N-1} - r_N)(1\uparrow)(2\downarrow) \cdots (N-1\uparrow)(N\downarrow)] \quad (2)$$

where

$$\phi(r) = \sum_k \frac{v_k}{u_k} e^{i\mathbf{k}\cdot\mathbf{r}} \quad (3)$$

and both wavefunctions lead to the same result for a large system. Nevertheless, ϕ_N is more helpful for understanding the underlying physics related to the magnetic impurity effect in superconductors: we are concerned with a bound state of Cooper pairs in a BCS condensate. It should be noticed that the (bounded) pair wavefunction $\phi(r)$ and the BCS pair-correlation amplitude $I(r)$ ³⁷ are basically the same for large N:

$$\phi(r) = \sum_k \frac{\Delta_k}{\epsilon_k + E_k} e^{i\mathbf{k}\cdot\mathbf{r}}, \quad (4)$$

$$I(r) = \sum_k \frac{\Delta_k}{2E_k} e^{i\mathbf{k}\cdot\mathbf{r}} \sim \Delta K_0\left(\frac{r}{\pi\xi_0}\right), \quad (5)$$

where

$$E_k = \sqrt{\epsilon_k^2 + \Delta_k^2}. \quad (6)$$

Here K_0 is a modified Bessel function which decays rapidly when $r > \pi\xi_0$.

In the presence of magnetic impurities, BCS pairing must employ degenerate partners which have the exchange scattering (due to magnetic impurities) built in because the strength of exchange scattering J is much larger than the binding energy. This scattered state representation was first introduced by Anderson³⁹ in his theory of dirty superconductors. Accordingly, the corresponding wavefunctions are

$$\tilde{\phi}' = \prod_n (u_n + v_n a_{n\uparrow}^\dagger a_{\bar{n}\downarrow}^\dagger) \phi_0 \quad (7)$$

and

$$\phi'_N = A[\phi'(r_1, r_2) \phi'(r_3, r_4) \cdots \phi'(r_{N-1}, r_N)] \quad (8)$$

where

$$\phi'(r_1, r_2) = \sum_n \frac{v_n}{u_n} \psi_{n\uparrow}(r_1) \psi_{\bar{n}\downarrow}(r_2). \quad (9)$$

Here $\psi_{n\uparrow}$ and $\psi_{\bar{n}\downarrow}$ denote the exact eigenstate and its degenerate partner, respectively. It is clear from the pair wavefunction $\phi'(r_1, r_2)$ that only the magnetic impurities within ξ_0 of a Cooper pair's center of mass can diminish the pairing interaction.

B. Phonon-mediated matrix element

Now we need to determine the scattered state ψ_n and the phonon-mediated matrix element $V_{nn'}$. The magnetic interaction between a conduction electron at $\mathbf{r}$ and a magnetic impurity (having spin $\mathbf{S}$), located at $\mathbf{R}_i$, is given by

$$H_m(\mathbf{r}) = J\mathbf{s} \cdot \mathbf{S}_i v_o \delta(\mathbf{r} - \mathbf{R}_i), \quad (10)$$

where $\mathbf{s} = \frac{1}{2}\sigma$ and v_o is the atomic volume. The scattered basis state which carries the label, $n\alpha = \vec{k}\alpha$, is then

$$\psi_{n\alpha=\vec{k}\alpha} = N_{\vec{k}} [e^{i\vec{k}\cdot\vec{r}} \alpha + \sum_{\vec{q}} e^{i(\vec{k}+\vec{q})\cdot\vec{r}} (W_{\vec{k}\vec{q}} \beta + W'_{\vec{k}\vec{q}} \alpha)], \quad (11)$$

where,

$$W_{\vec{k}\vec{q}} = \frac{\frac{1}{2}J\bar{S}v_o}{\epsilon_{\vec{k}} - \epsilon_{\vec{k}+\vec{q}}} \sum_j \sin\chi_j e^{i\phi_j - i\vec{q}\cdot\mathbf{R}_j} \quad (12)$$

and,

$$W'_{\vec{k}\vec{q}} = \frac{\frac{1}{2}J\bar{S}v_o}{\epsilon_{\vec{k}} - \epsilon_{\vec{k}+\vec{q}}} \sum_j \cos\chi_j e^{-i\vec{q}\cdot\mathbf{R}_j}. \quad (13)$$

χ_j and ϕ_j are the polar and azimuthal angles of the spin $\mathbf{S}_j$ at $\mathbf{R}_j$ and $\bar{S} = \sqrt{S(S+1)}$. The perturbed basis state for the degenerate partner of (11) is:

$$\psi_{\bar{n}\beta=-\vec{k}\beta} = N_{\vec{k}}[e^{-i\vec{k}\cdot\vec{r}}\beta + \sum_{\vec{q}} e^{-i(\vec{k}+\vec{q})\cdot\vec{r}}(W_{\vec{k}\vec{q}}^*\alpha - W_{\vec{k}\vec{q}}'\beta)]. \quad (14)$$

At each point $\vec{r}$, the two spins of the degenerate partner become canted by the mixing of the plane wave and spherical-wavelet component. Consequently, the BCS condensate is forced to have a triplet component because of the canting caused by the exchange scattering. The phonon-mediated matrix element between the canted basis pairs is (to order J^2)

$$V_{nn'} \equiv V_{\vec{k}'\vec{k}} = -V < \cos\theta_{\vec{k}'}(\vec{r}) > < \cos\theta_{\vec{k}}(\vec{r}) >, \quad (15)$$

where θ is the canting angle. The angular brackets indicate both a spatial and impurity average. It is then given

$$< \cos\theta_{\vec{k}}(\vec{r}) > \cong 1 - 2|W_{\vec{k}}|^2, \quad (16)$$

where $|W_{\vec{k}}|^2$ is the relative probability contained in the virtual spherical waves surrounding the magnetic solutes (compared to the plane-wave part). From Eqs. (11)-(13) we obtain

$$|W_{\vec{k}}|^2 = \frac{J^2 m^2 \bar{S}^2 c_m R}{8\pi n \hbar^4}, \quad (17)$$

where c_m is the magnetic solute fraction. Because the pair-correlation amplitude falls exponentially as $\exp(-r/\pi\xi_0)^{37}$ at $T = 0$ and as $\exp(-r/3.5\xi_0)^{40}$ near T_c , we set

$$R = \frac{3.5}{2}\xi_0. \quad (18)$$

Then one finds

$$< \cos\theta > = 1 - \frac{3.5\xi_0}{2\ell_s}, \quad (19)$$

where $\ell_s = v_F\tau_s$ is the mean free path for exchange scattering only.

C. BCS T_c equation

The resulting BCS gap equation, near T_c , is given by

$$\overline{\Delta_{\vec{k}}} = - \sum_{\vec{k}'} \overline{V_{\vec{k},\vec{k}'}} \frac{\overline{\Delta_{\vec{k}'}}}{2\overline{\epsilon_{\vec{k}'}}} \tanh\left(\frac{\overline{\epsilon_{\vec{k}'}}}{2T}\right). \quad (20)$$

Here $\overline{\Delta_k}$ is the impurity averaged value of the gap parameter whereas $\overline{\epsilon_k}$ is that of the electron energy. The BCS T_c equation still applies after a modification of the effective coupling constant according to Eq. (15):

$$\lambda_{eff} = \lambda \langle \cos\theta \rangle^2, \quad (21)$$

where λ is $N_o V$. Accordingly, the BCS T_c equation is now,

$$k_B T_c = 1.13 \hbar \omega_D e^{-\frac{1}{\lambda_{eff}}}. \quad (22)$$

The initial slope is given

$$k_B(\Delta T_c) \cong -\frac{0.63\hbar}{\lambda\tau_s}. \quad (23)$$

The factor $1/\lambda$ shows that the initial slope depends on the superconductor and is not a universal constant. For an extended range of solute concentration, KO find

$$\langle \cos\theta \rangle = \frac{1}{2} + \frac{1}{2}[1 + 5(\frac{u}{2})^2]^{-1}e^{-2u}, \quad (24)$$

where

$$u \equiv 3.5\xi_{eff}/2\ell_s. \quad (25)$$

We have replaced ξ_0 by the effective coherence length ξ_{eff} which is explained below.

D. Change of the initial slope of the T_c decrease

When the conduction electrons have a mean free path ℓ which is smaller than the coherence length ξ_0 (for a pure superconductor), the effective coherence length is

$$\xi_{eff} \approx \sqrt{\ell\xi_0}. \quad (26)$$

For a superconductor which has ordinary impurities as well as magnetic impurities, the total mean-free path ℓ is given by

$$\frac{1}{\ell} = \frac{1}{\ell_s} + \frac{1}{\ell_0}, \quad (27)$$

where ℓ_0 is the mean free path for the potential scattering. It is evident from Eq. (26) that the potential scattering profoundly affects the paramagnetic impurity effect. Consequently, the initial slope of the T_c depression is decreased in the following way:

$$k_B(\Delta T_c) \cong -\frac{0.63\hbar}{\lambda\tau_s} \sqrt{\frac{\ell}{\xi_0}}. \quad (28)$$

This explains the broad scattering of the experimental $-dT_c/dc$ values. In other words, the size of the Cooper pair is reduced by the potential scattering and the reduced Cooper pair

sees a smaller number of magnetic impurities. Accordingly, the magnetic impurity effect is partially suppressed, leading to the decrease of the initial slope of the T_c depression.

Figure 1 shows the different behavior of the T_c depression due to magnetic impurities in the pure crystalline state and in the amorphous or disordered state of superconductors. We used $T_{c0} = 1.0K$, $v_F = 1.5 \times 10^8 cm/sec$, and $\omega_D = 250K$. We also assumed the relation between ℓ_s and magnetic impurity concentration c : $\ell_s = 10^5/c(\text{\AA})$. Here c is measured in at %. Since the exchange scattering cross-section is usually 20-200 times smaller than that for the potential scattering,¹¹ this assumption seems to be reasonable. For the pure crystalline state T_c drops to zero suddenly when T_c is decreased to about 50 % of T_{c0} of the pure system, which may be called *pure limit behavior*. As the mean free path ℓ is decreased due to disorder, the initial T_c depression is weakened and T_c drops to zero more slowly near the critical concentration.

IV. COMPARISON WITH EXPERIMENT

The overall agreement between KO theory and the existing experimental data is impressive. We focus on the experiments which investigated the difference of the magnetic impurity effect in pure crystalline state and amorphous or disordered state of superconductors.

A. *Pure limit behavior: Roden and Zimmermeyer's Experiment*

Roden and Zimmermeyer⁶ prepared alloys of Cd with dilute Mn impurities by quench condensation. Quench condensation produces a variety of states of the alloy: in particular, one can get a microcrystalline and an amorphous state. A quench-condensed film of Cd in the microcrystalline state shows a higher T_c ($= 0.9K$) than the bulk material ($T_c = 0.55K$) and a further increase of T_c ($= 1.15K$) is obtained in the amorphous state. Amorphous Cd film was obtained by adding Cu atoms. Like other nontransition metals deposited in an ordinary high-vacuum system, quench-condensed Cd film is crystalline with small crystallites.⁴¹

Now we compare KO theory with Roden and Zimmermeyer's experiment. Figure 2 shows T_c versus magnetic impurity concentration c in the microcrystalline CdMn. The solid line is theoretical curve obtained from Eq. (22). The transition temperature T_{c0} of pure Cd in this state is 0.9K. While the initial depression of T_c is linear in c with a value of $-dT_c/dc = 5.4K/at\%$, above 0.05% the depression becomes much more stronger than linear, which agrees with KO theory. Arrows denote that no superconductivity was found up to 70mK. For theoretical fitting we used $T_{c0} = 0.904K$, $\omega_D = 209K$, and $v_F = 1.62 \times 10^8 cm/sec$.⁴² We emphasize that there is no free parameter. But, in the absence of experimental data we assumed $\ell_s = 9 \times 10^5/c$ ($\text{\AA}$). As can be seen, the agreement between the experimental data and the theoretical curve is very good.

Figure 3 shows T_c vs. c for the amorphous CdCuMn. The solid line was obtained from Eqs. (22) and (26). The decrease of T_c for smaller c is again linear but with a much lower $-dT_c/dc = 2.65K/at\%$. In the amorphous state T_{c0} is about 1.18K. Since the residual resistivity data are not available, we assumed that the mean free path for the potential scattering is $\ell_0 = 4500\text{\AA}$ which is reasonable. We used the same values for ω_D and v_F as in Fig. 2. Again we find a good fitting to experimental data.

B. Change of the initial slope of the T_c depression

Schlabitx and Zaplinski⁷ reported measurements of the T_c -depression of ZnMn single crystals. In particular, they investigated the influence of lattice defects on the T_c -depression in dilute ZnMn single crystals. They demonstrated linear behavior up to a concentration of 10 ppm with a slope of 630 K/at%. This value is twice that of other measurements. As a result, they suggested that the T_c -depression can be enhanced strongly by eliminating the lattice defects.

Figure 4 shows the reduced transition temperature, T_c/T_{c0} , as a function of Mn concentration for ZnMn samples. The dashed lines, taken from the other measurements,¹³ give the T_c -depression of: a) quench-condensed films, and b) cold rolled bulk material. The filled points represent the T_c -values of the ZnMn single crystals. The filled squares are the data of quench condensed thin films, while the filled triangles are the data of quench condensed thin films after annealing at 300K for 14 hours. Since annealing leads to an increased order of the lattice,⁴¹ it is clear that the initial slope of the T_c decrease is decreasing as the system is getting disordered.

The solid line is the theoretical curve obtained from the initial slope, $-dT_c/dc = 630K/at\%$ with $T_{c0} = 0.9K$:

$$k_B T_c \cong k_B T_{c0} - \frac{0.63\hbar}{\lambda\tau_s}. \quad (29)$$

This expression agrees very well with the exact BCS T_c equation, Eq. (22), up to 25 % of the critical impurity concentration. The dashed lines (a) and (b) can also be reproduced from the theoretical formula, Eq. (28),

$$k_B T_c \cong k_B T_{c0} - \frac{0.63\hbar}{\lambda\tau_s} \sqrt{\frac{\ell}{\xi_0}}, \quad (30)$$

for the initial T_c depression in the disordered state of superconductors with (a) $\ell = 7520\text{\AA}$, $T_{c0} = 0.83K$,¹³ and (b) $\ell = 3390\text{\AA}$, $T_{c0} = 1.51K$,¹³ respectively. Here T_{c0} values are the experimental results.¹³ Therefore, the change of the initial slope of the T_c decrease may be explained in terms of the change of the Cooper pair size caused by the variation of the mean free path ℓ . We used $\omega_D = 327K$, and $v_F = 1.82 \times 10^8 cm/sec$.⁴² The sudden drop of T_c near the critical concentration is not pronounced though, presumably because of the smallness of the critical concentration. Since there are not many magnetic impurities in the Zn matrix, the distribution of Mn may be atomically disperse but macroscopically inhomogeneous. Then, the *pure limit behavior* may not be observable.

Bauriedl and Heim⁵ investigated the influence of lattice disorder on the magnetic properties of InMn alloys. Crystalline In films were implanted by Mn ions. The amount of lattice disorder was changed in a very controlled way by pre-implantation of indium with its own ions, which was very effective in producing disordered films.

Figure 5 shows the transition temperatures for InMn alloys with increasing lattice disorder from 1 to 3 by pre-implantation of In^+ ions: 1 0ppm; 2 2660ppm; 3 18,710ppm. These ions have an intensive damaging effect, resulting in an increased residual resistivity and an enhanced transition temperature T_{c0} .⁵ Notice that the initial slope decreases as the system is more disordered. The solid lines are the theoretical results from Eq. (28) with 1 $\ell = 1050\text{\AA}$,

$2\ell = 700\text{\AA}$ and $3\ell = 150\text{\AA}$. It is necessary to emphasize that the change of the initial slope due to the enhanced T_{c0} (Eq. (23)) is not enough to explain the experimental data. We assumed the initial slope $-dT_c/dc = 53K/at\%$ for a pure system.³¹ We also used $\omega_D = 108K$ and $v_F = 1.74 \times 10^8$.⁴² We find good agreements between theory and experiment.

Finally, Habisreuther et al.⁹ investigated the magnetic behavior of Mn in crystalline β -Ga and amorphous a -Ga films. Mn ions were implanted at low temperature ($T < 10K$). The amorphous a -Ga exhibits a rather high transition temperature with typical values between 8.1 and 8.4 K, while the crystalline β -Ga phase shows transition temperature of $T_c = 6.3K$.

Figure 6 shows changes of the superconducting transition temperature ΔT_c produced by Mn implantation into amorphous a -Ga films and crystalline β -Ga films as a function of the impurity concentrations. Note that the initial slope 3.4 K/at % in amorphous a -Ga is about half of that (7.0 K/at %) in crystalline β -Ga films. Theoretical curves represent the initial slope formulas, Eq. (23) and (28) with $-dT_c/dc = 7K/at\%$, $\ell = \infty$ for β -Ga, and with $-dT_c/dc = 7K/at\%$, $\ell = 600\text{\AA}$ for a -Ga. We used $\omega_D = 320K$ and $v_F = 1.91 \times 10^8 cm/sec$.⁴² A good fitting to the experimental data is obtained.

V. DISCUSSION

It is clear that a systematic experimental study of the effect of magnetic impurities in crystalline and amorphous superconductors is necessary. In particular, the *pure limit behavior* in a crystalline state of superconductors and the change of the initial slope due to disordering need more careful studies. This study may shed a new light on the old question of whether a transition metal impurity possesses a stable local magnetic moment within a metallic host.

The observed *pure limit behavior* in the superfluid He-3 in aerogel may be compared with that in crystalline superconductors including Cd. In superfluid He-3 aerogel does not disturb the liquid state of He-3 significantly, whereas in superconductors adding magnetic impurities may damage the crystalline state of the superconductors, resulting in the difficulty in observing the *pure limit behavior*.

In our theoretical fitting we guessed the mean free path ℓ because the experimental residual resistivity data were not available. If the residual resistivity is given, the mean free path ℓ can be determined from the Drude formula. It is interesting to note that the initial T_c depression also provides a way to estimate the mean free path ℓ .

In this study, weak-coupling BCS theory is used to investigate the effect of magnetic impurities in superconductors. It is straightforward to extend this study to the strong-coupling theory.^{43,44} To do that, pairing of the degenerate scattered state partners is also needed.⁴⁵ The result will then basically be the same as that of the weak-coupling theory. More details will be published elsewhere.

VI. CONCLUSION

The effect of magnetic impurities in crystalline and amorphous states of superconductors has been studied theoretically. The *pure limit behavior* in crystalline Cd observed by Roden

and Zimmermeyer and the decrease of the initial slope of the T_c depression due to disorder have been explained. In particular, the initial slope of the T_c decrease is decreasing by a factor $\sqrt{\ell/\xi_0}$ as the system is getting disordered. We suggest that a more systematic experimental investigation is necessary for the different behavior of the magnetic impurities in crystalline and amorphous superconductors. Such an investigation may also be important for understanding whether a transition metal impurity possesses a magnetic moment in a metallic host or not.

ACKNOWLEDGMENTS

Y.J.K. is grateful to Department of Physics at UPR-Humacao where this work was finished. M. Park thanks the FOPI at the University of Puerto Rico-Humacao for release time.

REFERENCES

- ¹ M. F. Merriam, S. H. Liu, and D. P. Seraphim, Phys. Rev. **136**, A17 (1964).
- ² G. Boato, G. Gallinaro, and C. Rizzuto, Phys. Rev. **148**, 353 (1966).
- ³ E. Wassermann, Z. Phys. **220**, 6 (1969).
- ⁴ W. Bauriedl and G. Heim, Z. Phys. B **26**, 29 (1977).
- ⁵ M. Hitzfeld and G. Heim, Solid State Commun. **29**, 93 (1979).
- ⁶ B. Roden and G. Zimmermeyer, J. Low Temp. Phys. **25**, 267 (1976).
- ⁷ W. Schlabititz and P. Zaplinski, in *Proc. of 14th Int. Conf. Low Temp. Phys. Helsinki*, 1975, Vol. 3, p. 452.
- ⁸ A. Hofmann, W. Bauriedl, and P. Ziemann, Z. Phys. B **46**, 117 (1982).
- ⁹ T. Habisreuther, W. Miehe, A. Plewnia, and P. Ziemann, Phys. Rev. B **46**, 14566 (1992).
- ¹⁰ W. Buckel, *Superconductivity: Fundamentals and Applications*, (VCH, Weinheim, 1991), p. 212.
- ¹¹ Yong-Jihn Kim and A. W. Overhauser, Phys. Rev. **49**, 15799 (1994).
- ¹² Mi-Ae Park, M. H. Lee, and Yong-Jihn kim, Physica C **306**, 96 (1998).
- ¹³ H. Falke, H. P. Jablonski, J. Kästner, and E. F. Wassermann, Z. Phys. **259**, 135 (1973).
- ¹⁴ G. Boato, G. Gallinaro, and C. Rizzuto, Rev. Mod. Phys. **36**, 162 (1964).
- ¹⁵ D. L. Martin, Phys. Rev. **167**, 640 (1968).
- ¹⁶ W. Smith, J. Low Temp. Phys. **5**, 683 (1971).
- ¹⁷ H. Sanchez, Thesis, Rutgers University, New Brunswick, N. J., (1972).
- ¹⁸ F. T. Hedgcock and C. Rizzuto, Phys. Lett. **24** A, 17 (1966).
- ¹⁹ P. J. Ford, C. Rizzuto, and C. Salamoni, Phys. Rev. B **6**, 1851 (1972).
- ²⁰ J. V. Porto and J. M. Parpia, Phys. Rev. Lett. **74**, 4667 (1995).
- ²¹ D. T. Sprague, T. M. Haard, J. B. Kycia, M. R. Rand, Y. Lee, P. J. Hamot, and W. P. Halperin, Phys. Rev. Lett. **75**, 661 (1995).
- ²² K. Matsumoto, J. V. Porto, L. Pollack, E. N. Smith, T. L. Ho, and J. M. Parpia, Phys. Rev. Lett. **79**, 253 (1997).
- ²³ M. B. Maple, J. Appl. Phys. **9**, 179 (1976).
- ²⁴ M. A. Jensen and H. Suhl, in *Magnetism: A Treatise on Modern Theory and Materials*, edited by G. T. Rado and H. Suhl (Academic, New York, 1966), Vol. II B, p. 183.
- ²⁵ K. Schwidtal, Z. Phys. **158**, 563 (1960).
- ²⁶ A. A. Abrikosov and L. P. Gor'kov, Zh. Eksp. Teor. Fiz. **39**, 1781 (1961) [Sov. Phys. JETP **12**, 1243 (1961)].
- ²⁷ N. Barth, Z. Phys. **148**, 646 (1957).
- ²⁸ W. Buckel, M. Dietrich, G. Heim, and J. Kessler, Z. Phys. **245**, 283 (1971).
- ²⁹ A. Schertel, Phys. Verh. **2**, 102 (1951).
- ³⁰ P. Ziemann, Festkörperprobleme **XXIII**, 93 (1983).
- ³¹ W. Opitz, Z. Phys. **141**, 263 (1955); A. W. Bjerkaas, D. M. Ginsberg, and B. J. Mostik, Phys. Rev. B **5**, 854 (1972).
- ³² F. Reif and M. A. Woolf, Phys. Rev. Lett. **9**, 315 (1962).
- ³³ B. T. Matthias, H. Suhl, and E. Corenzwit, Phys. Rev. Lett. **1**, 92 (1958).
- ³⁴ K. Schwidtal, Z. Phys. **169**, 564 (1962).
- ³⁵ F. T. Hedgcock, S. N. Mahajan, and C. Rizzuto, J. Appl. Phys. **39**, 851 (1968).
- ³⁶ G. Zimmermeyer and B. Roden, Z. Phys. B **24**, 377 (1976).
- ³⁷ J. Bardeen, L. N. Cooper, and J. R. Schrieffer, Phys. Rev. **108**, 1175 (1957).

- ³⁸ P. G. de Gennes, *Superconductivity of Metals and Alloys* (Benjamin, New York, 1966), ch. 4.
- ³⁹ P. W. Anderson, J. Phys. Chem. Solids, **11**, 26 (1959).
- ⁴⁰ P. W. Anderson and P. Morel, Phys. Rev. **123**, 1911 (1961).
- ⁴¹ C. G. Granqvist and T. Claeson, J. Low Temp. Phys. **10**, 735 (1973).
- ⁴² C. Kittel, *Introduction to Solid State Physics* (John Wiley, New York, 1976), chs. 5 and 6.
- ⁴³ G. M. Eliashberg, Zh. Eksp. Teor. Fiz. **38**, 966 (1960) [Sov. Phys. JETP **11**, 696 (1960)].
- ⁴⁴ W. L. McMillan, Phys. Rev. **167**, 331 (1968).
- ⁴⁵ Yong-Jihn Kim, Mod. Phys. Lett. B **10**, 555 (1996).

Table I. Values for the initial depression $-(dT_c/dc)_{initial}$ of the T_c of Zn with different concentrations of Mn. Data are from Falke et al., Ref. 13.

$-(dT_c/dc)_{initial}$ in [K/at %]	sample	Reference
170	bulk	[14] (1964)
315	bulk	[2] (1966)
>300	bulk	[15] (1968)
260 (290)	bulk	[16] (1971)
300	bulk	[17] (1972)
630	single crystal	[7] (1975)
215	thin film	[18] (1967)
285	thin film	[13] (1967)

Table II. Reduction in the T_c of some superconductors by magnetic impurities. Data are from Buckel, Ref. 10, Wassermann, Ref. 3, and Schwidtal, Ref. 25.

Superconductor	Additive	$-dT_c/dc$ in K/atom %			
Pb	Mn	21* a), 16** b)			
Sn	Mn	69* c), 14** b)			
Zn	Mn	315 d),	285* e),	343** f),	630 g)
Zn	Cr	170 d), 90-200 h)			
Cd	Mn	44 i), 5.4* j)			
In	Mn	25 k),	53* l),	50** m),	100 n)
In	Fe	2.5 l), 2.0 o)			
La	Gd	5.1* p), 4.5** q)			

* quench-condensed films

** ion implantation at low temperatures

References: a): [27]; b):[28]; c):[29]; d):[2]; e):[13]; f):[30]; g):[7];

h):[3]; i):[18]; j):[6]; k):[4]; l):[31]; m):[8]; n):[1]; o):[32]; p):[33]; q):[34];

FIGURES

FIG. 1. Variation of T_c with magnetic impurity concentration for pure and impure superconductors. ℓ_o denotes the mean free path for the potential scattering.

FIG. 2. Comparison of the experimental data for CdMn in the microcrystalline state with the KO theory. Data are from Roden and Zimmermeyer, Ref. 6.

FIG. 3. Comparison of the experimental data for CdMn in the amorphous state with the KO theory. Data are from Roden and Zimmermeyer, Ref. 6.

FIG. 4. Reduced transition temperature versus Mn concentration for ZnMn. The solid line represents the theoretical curve obtained from Eq. (29). Line (a): Data of thin films from Ref. 13, line (b): Data of cold rolled bulk material from Refs 2 and 16. Data are from Schlabitzi and Zaplinski, Ref. 7.

FIG. 5. Calculated transition temperatures for implanted InMn alloys. Increasing lattice disorder from 1 to 3 has been produced by pre-implantation of In ions: 1 0ppm, 2 2660 ppm, 3 18,710 ppm. Data are from Bauriedl and Heim, Ref. 4.

FIG. 6. Calculated changes of the superconducting transition temperature ΔT_c versus impurity concentration for Mn-implanted amorphous α -Ga and crystalline β -Ga. Data are from Habisreuther et al., Ref. 9.











